



AQUA-CURE VOX

LOW ODOR, WATER-BASED CURE AND SEAL

DESCRIPTION

AQUA-CURE VOX is a water-based acrylic polymer curing and sealing compound. **AQUA-CURE VOX** is suitable for use over new and old concrete and performs well on both interior and exterior surfaces. It enables fresh concrete to maintain adequate moisture, seals the surface, and provides an attractive sheen.

PRIMARY APPLICATIONS

- Hospitals
- Exterior concrete
- Walls
- Industrial floors
- Basements & footings
- Interior & exterior concrete surfaces
- Pavements

FEATURES / BENEFITS

- Forms an efficient moisture barrier for optimum curing of concrete
- Seals concrete surfaces to protect against the effects of weathering
- Increases durability by promoting proper cement hydration
- Helps prevent dusting of new concrete
- Dries to a clear transparent film that resists yellowing under exterior or ultraviolet exposure
- Gives an alternative to solvent based materials where fumes may be objectionable, undesirable, or non-compliant

TECHNICAL INFORMATION

Typical Engineering Data

The following results were developed under laboratory conditions @ 50% RH.

Drying Time*	1 to 2 hours
Recoat Time**	2 to 4 hours
Foot Traffic	4 to 6 hours
Wheel Traffic	6 to 10 hours
Solids content	15%
Moisture loss (ASTM C 156)	< 0.55 kg/m ²

* Low concrete or air temperatures and/or high relative humidity will extend the drying time.

** If a second coat will be applied, application must be within 4 hours to ensure proper intercoat adhesion.

Heavy applications, application in cool, cold, or humid conditions, or prolonged exposure to moisture may cause **AQUA-CURE VOX** to be powdery or have a milky-white appearance. Follow all application instructions carefully.

Appearance: **AQUA-CURE VOX** is a white, opaque liquid. After proper application and drying, the film is clear with a slight glossy appearance.

PACKAGING

AQUA-CURE VOX is packaged in 20L jerry cans and 200L plastic drums.

SHELF LIFE

1 year in original, unopened container.

SPECIFICATIONS / COMPLIANCES

- ASTM C 309, Type 1, Class A & B

COVERAGE

Application: m ² /L	First Coat	Optional Second Coat
Curing and sealing new concrete	5.0 to 7.5	7.5 to 10.0
Use on existing, cured concrete	6.0 to 8.5	8.5 to 11.0

Coverage will vary from the above rates depending on surface porosity and texture.

AVOID EXCESSIVE BUILD-UP. THICKER APPLICATIONS MAY LEAD TO DISCOLORATION AND POOR PRODUCT PERFORMANCE.

DIRECTIONS FOR USE

Surface Preparation: The concrete surface must be clean and free of standing water. Remove any sealer or other material that may prevent adhesion of the **AQUA-CURE VOX**.

Mixing: **AQUA-CURE VOX** requires no preblending and should be used directly from the container.

Application: Apply at a uniform coverage by spray or roller application. Product may be sprayed with a hand held “pump-up” sprayer or with an airless industrial sprayer. If roller applied, use a 9 mm nap sleeve. Do not apply heavily - follow coverage rates carefully.

Curing and Sealing: For the best cure of freshly placed concrete, apply **AQUA-CURE VOX** as soon as possible after finishing operations and/or immediately after the disappearance of the “sheen” of surface moisture. When applying to old concrete, remove contaminants and stains such as waxes, grease and oil with strong soaps or caustics rather than acids. Apply **AQUA-CURE VOX** at recommended coverage rates. If a second coat is desired, apply within 2 to 4 hours of the previous coat.

CLEAN UP

Clean tools and equipment with warm, soapy water before the material has dried.

REMOVAL

Dried, cured **AQUA-CURE VOX** may be removed with strong solvents such as xylene, MEK or toluene. Also acceptable are commercial paint strippers (always heed directions and warning labels). Alternatively, the sealer can be removed by sandblasting or by other similar mechanical means.

PRECAUTIONS / LIMITATIONS

- Do not allow containers of product to freeze. Store between 10°C to 38°C.
- For best application results, product temperature should be between 10°C to 38°C with ambient and surface temperatures between 7°C to 35°C during application.
- Do not apply over concrete that may receive concrete toppings, epoxy coatings, or urethane coatings.
- Although compatible with many carpet, tile and floor covering adhesives, a test section is recommended to ensure good bond between the adhesive and **AQUA-CURE VOX**. Complete product removal or the use of **KUREZ DR VOX** is recommended to cure concrete in areas to receive movable carpet squares.
- Do not use as a bond breaker for tilt-up construction.
- Do not subject concrete to rain or other sources of water for at least 12 hours after application.
- Do not thin this product with water or any other solvents.
- In all cases, consult the Safety Data Sheet before use.

Rev: 30/06/20