



TREMprime QD LV

A Quick Drying, VOC Compliant Asphaltic Primer

DESCRIPTION

TREMprime QD LV is formulated from refined asphalt to produce an effective priming base for the application of hot rubberized asphalt waterproofing membranes, torch down waterproofing membranes and asphaltic based self-adhesive waterproofing membranes.

BASIC USES

TREMprime QD LV can be used as a primer for concrete and weathered bituminous roofing membranes. It can also be used as a metal primer for liquid applied asphaltic waterproofing membranes.

FEATURES & BENEFITS

- Less than 300 g/liter VOC
- Single component, ready to use as received
- Quick drying

PACKAGING

20L pails

SHELF LIFE

In the original unopened packaging the primer has an 18 month shelf life from the date of manufacture.

STORAGE

Store in a cool dry area at temperatures between +5°C and +30°C.

DIRECTIONS FOR USE

- Stir the TREMprime QD LV well before application. Some separation can occur during storage. If the primer is not mixed well before application, it can have an adverse impact on adhesion.

- Substrate must be clean, dry and free from any surface contamination.
- New concrete must be cured for at least 28 days.
- Can be applied by brush, roller or spray. But if spray application is used extreme care must be taken to avoid overspray and contamination of adjacent buildings and vehicles.
- Ensure that the surface is totally dry before applying the primer. If the substrate has a high moisture content it can cause bubbling and blistering of the next layer that is applied.
- If the substrate is very porous it may be necessary to apply two coats of TREMprime QD LV.
- Do not puddle the primer. If the primer is applied too thick, solvent may get trapped in the primer which can cause blistering in the next lay of waterproofing that is applied.
- Allow the solvent to evaporate from the primer before application of subsequent layers. Failure to allow the solvent to completely evaporate can lead to blistering of the waterproofing layer.
- The application temperature range for the primer is between +5°C and +40° C.
- Tools should be cleaned with white spirits.

Dilution

This primer was formulated to meet VOC requirements of < 350 g/liter. Dilution is not recommended in jurisdictions which have VOC regulations that require < 350 g/liter VOC. If you have questions about this, please contact your local Tremco Technical Sales Representative.

Coverage

80 to 100m²/20 liter pail per coat of TREMprime QD LV.

WARRANTY

Tremco CPG APAC products are manufactured to rigid standards of quality. Any product which has been applied (a) in accordance with Tremco CPG APAC written instructions and (b) in any application recommended by Tremco CPG APAC, but which is proved to be defective, will be replaced free of charge. No liability can be accepted for the information provided in this leaflet although it is published in good faith and believed to be correct. Tremco CPG APAC reserves the right to alter product specifications without prior notice, in line with Company policy of continuous development and improvement.

TECHNICAL DATA

Characteristic	Value
Appearance	Dark brown to black low viscosity liquid with a characteristic solvent odor.
Density at +23°C	0.87-0.91 g/ml
VOC Content	< 300 g/liter (US EPA Method 24)
Flash Point	+ 32°C minimum (Abel closed cup)
Drying Time	1-3 hours at 25°C

To find your local office address and contact details, visit

www.tremcocpg-asiapacific.com