



TREMCO ANTIROOT ADDITIVE

Antiroot Additive for TREMproof 250GC and TREMproof 60

DESCRIPTION

Antiroot Additive for TREMproof 250GC and TREMproof 60.

BASIC USES

While Tremco Antiroot Additive will provide resistance to most root systems, it is always recommended that plants with non-invasive root systems be used in planter boxes and general landscape projects.

FEATURES & BENEFITS

- Protects construction materials from undesirable root penetration without damaging plants.
- Provides long-term protection.
- Remains effective also under harsh weathering conditions.
- Is heat-resistant and has a very low vapour pressure. The effectiveness of the active ingredient is virtually unaffected by the high temperatures required to process bitumen and welding roofing felts.
- Has good compatibility with most bituminous construction materials.

PACKAGING

100ml Bottle

COLOUR

Amber

SHELF LIFE

Provided the product is correctly stored and kept in the original sealed package, its shelf life is at least 2 years.

DIRECTIONS FOR USE

Add full contents of bottle into pail and mix thoroughly for 5 minutes with a electric mechanical mixer. Apply TREMproof 250GC or TREMproof 60 in accordance with Tremco's Data Sheets.

CLEANING

- Excess sealant and smears adjacent to the joint interface can be carefully removed with Tremco Xylol before the sealant cures.
- Any utensils used for tooling can also be cleaned with Tremco Xylol, mineral spirits or white spirits.

SAFETY PRECAUTIONS

- Antiroot Additive is a viscous liquid. Contact of the product with the skin and the inhalation of vapours should be avoided. The precautions generally recommended for handling chemicals should be observed, eg. wearing of protective clothing, protective gloves and safety goggles. If the product comes into contact with the skin, the affected area should be washed immediately with large amounts of soap and plenty of water; splashes in the eye should be rinsed out immediately with plenty of water. If irritation persists, medical attention should be obtained. Contaminated clothing should be changed at once.
- The Safety Data Sheet (SDS) must be read and understood prior to use.

WARRANTY

Tremco warrants its Products to be free of defects in materials but makes no warranty as to appearance or colour. Since methods of application and on-site conditions are beyond our control and can affect performance, Tremco makes no other warranty, expressed or implied, including warranties of MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE with respect to Tremco Products. Tremco's sole obligation shall be, at its option, to replace or to refund the purchase of the quantity or Tremco product prove to be defective and Tremco shall not be liable for any loss or damage.

PROPERTY	TEST METHOD	TYPICAL VALUE
Density (20°C)		Approx. 1.21 g/cm ³
Solidification Point		Approx. -12°C
Boiling Point	DIN 53171	Above 300°C at 1013 hPa
Flash Point	DIN 22719	Approx. 242°C
Ignition Temperature	DIN 51794	Approx. 425°C
Solubility (20°C)		Slightly soluble in water, soluble in bitumen, tar pitches and organic solvents such as toluene and xylene

To find your local office address and contact details, visit

www.tremcocpg-asiapacific.com

REV21/10/20